

SOFPRENE® S221-65A

Easy to color, good for painting, very good technical properties.

Typical mechanical properties

Stress at break	551 psi	ISO 527-1/-2 or ISO 37
Elongation at break	520 %	ISO 527-1/-2 or ISO 37
Shore A hardness, 3s	65	ISO 48-4 / ISO 868
Tear strength, normal	137 lb/in	ISO 34-1

Other properties

Density	8 lb/gal	ISO 1183
---------	----------	----------

Additional information

Injection molding	Please note that the suggested temperatures are estimations. The actual desired temperatures can vary based on the molding machine design.
-------------------	--

Processing Texts

Longer pre-drying times/storage	The material must be stored indoors in the original, unopened and undamaged packaging, away from direct sunlight, moisture and heat.
---------------------------------	--

Injection molding	Please note that the suggested temperatures are estimations. The actual desired temperatures can vary based on the molding machine design.
-------------------	--
