

# LAPRENE® 8M3X5901A75

## Typical mechanical properties

|                       |           |                        |
|-----------------------|-----------|------------------------|
| Stress at break       | 522 psi   | ISO 527-1/-2 or ISO 37 |
| Elongation at break   | 300 %     | ISO 527-1/-2 or ISO 37 |
| Shore A hardness, 3s  | 75        | ISO 48-4 / ISO 868     |
| Tear strength, normal | 149 lb/in | ISO 34-1               |

## Other properties

|         |          |          |
|---------|----------|----------|
| Density | 8 lb/gal | ISO 1183 |
|---------|----------|----------|

## Injection

|                        |             |
|------------------------|-------------|
| Max. mould temperature | 68 - 122 °F |
|------------------------|-------------|

## Processing Texts

|                                 |                                                                                                                                      |
|---------------------------------|--------------------------------------------------------------------------------------------------------------------------------------|
| Longer pre-drying times/storage | The material must be stored indoors in the original, unopened and undamaged packaging, away from direct sunlight, moisture and heat. |
|---------------------------------|--------------------------------------------------------------------------------------------------------------------------------------|

---