

(+) 18816996168

Ponciplastics.com



# LAPRENE<sup>®</sup> 8MC5U..A70

## Typical mechanical properties

Stress at break	986 psi	ISO 527-1/-2 or ISO 37
Elongation at break	630 %	ISO 527-1/-2 or ISO 37
Shore A hardness, 3s	70	ISO 48-4 / ISO 868

## Other properties

Density	10 lb/gal	ISO 1183
---------	-----------	----------

## Injection

Max. mould temperature	68 - 122 °F
------------------------	-------------

## Processing Texts

Longer pre-drying times/storage      The material must be stored indoors in the original, unopened and undamaged packaging, away from direct sunlight, moisture and heat.