

## PIBIFLEX® E6067T - TPC

### Description

PIBIFLEX® E6067T is a nominal 57 Shore D thermoplastic polyester elastomer with heat stabilization that is for extrusion molding applications and use as a performance modifier for TPE compounding.

### Physical properties

ISO	Value	Unit	Test Standard
Density	1220	kg/m <sup>3</sup>	ISO 1183

### Mechanical properties

ISO	Value	Unit	Test Standard
Tensile stress at break, 50mm/min	39	MPa	ISO 527-2/1A
Tensile strain at break, 50mm/min	>500	%	ISO 527-2/1A
Flexural modulus, 23°C	345	MPa	ISO 178
Charpy notched impact strength, 23°C	NB	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy notched impact strength, -30°C	NB	kJ/m <sup>2</sup>	ISO 179/1eA
Izod impact notched, 23°C	NB	kJ/m <sup>2</sup>	ISO 180/1A
Izod impact notched, -30°C	NB	kJ/m <sup>2</sup>	ISO 180/1A
Shore D hardness, 15s	57	-	ISO 868

### Thermal properties

ISO	Value	Unit	Test Standard
Melting temperature, 10°C/min	215	°C	ISO 11357-1/-3

### Typical injection moulding processing conditions

#### Pre Drying

	LowMaxRes	DryTime	DryTemp
max	0.05 %	4 h	110 °C
min			100 °C

#### Temperature

	Hopper
max	50 °C
min	20 °C

### Other text information

#### Pre-drying

To avoid hydrolytic degradation during processing, PIBIFLEX TPC resins have to be dried to a moisture level equal to or less than 0.02%. Drying should be done in a dehumidifying hopper dryer capable of dewpoints <-40°F (-40°C) at 225°F (107°C) for 4 hours.

#### Longer pre-drying times/storage

For subsequent storage of the material in the dryer until processed (<= 24h) it is necessary to lower the temperature to 80° C.

### Characteristics

#### Product Categories

Tribological

#### Delivery Form

Pellets