

GUR® 5523

GUR®

Melt processable UHMW-PE pellet grade

Some of the listed data have been determined from the virgin powder.

Product information

Resin Identification	(PE-UHMW)	ISO 1043
Part Marking Code	>(PE-UHMW)<	ISO 11469
Average molecular weight	6.7E6 g/mol	Margolies' equation

Rheological properties

Viscosity number	3000 cm ³ /g	ISO 307, 1628
Intrinsic viscosity	2500	ISO 307, 1628

Typical mechanical properties

Tensile modulus	740 MPa	ISO 527-1/-2
Tensile stress at yield, 50mm/min	20 MPa	ISO 527-1/-2
Tensile strain at yield, 50mm/min	13 %	ISO 527-1/-2
Tensile stress at 50% strain	19 MPa	ISO 527-1/-2
Tensile stress at break, 50mm/min	38 MPa	ISO 527-1/-2
Nominal strain at break	410 %	ISO 527-1/-2
Elongational stress F, 150/10	0.24 MPa	ISO 21304-2
Charpy double notched impact strength, 23°C	160 kJ/m ²	ISO 21304-2
Poisson's ratio	0.46 ^[C]	

[C]: Calculated

Tribological properties

Wear by sandslurry method (based on GUR 4120=100)	110
--	-----

Thermal properties

Vicat softening temperature, 50°C/h 50N	80 °C	ISO 306
---	-------	---------

Physical/Other properties

Density	930 kg/m ³	ISO 1183
Bulk density	500 kg/m ³	ISO 60

Characteristics

Processing	Injection Moulding, Extrusion
Delivery form	Pellets
Special characteristics	High impact or impact modified, Hydrolysis resistant, Low wear / Low friction, Chemical resistant

GUR® 5523

GUR®

Additional information

Processing Notes

Pre-Drying

It is advised to pre-dry the material before processing. Recommended pre-drying conditions: 2 - 4 hours at 90 - 110°C. Please contact for further information.