

General Information				
Product Description				
GF-reinforced, Standard grade				
General				
Filler / Reinforcement	• Glass Fiber, 60% Filler by Weight			
Features	• General Purpose			
Uses	• Automotive Applications • Automotive Electronics		• Electrical/Electronic Applications • General Purpose	
ASTM & ISO Properties ¹				
Physical	Dry	Conditioned	Unit	Test Method
Density	1.79	--	g/cm³	ISO 1183
Melt Mass-Flow Rate (MFR)				ISO 1133
275°C/2.16 kg	9.4	--	g/10 min	
Melt Volume-Flow Rate (MVR)				ISO 1133
275°C/2.16 kg	5.3	--	cm³/10min	
Molding Shrinkage ²				Internal Method
Across Flow : 130°C, 2.00 mm	0.57	--	%	
Flow : 130°C, 2.00 mm	0.29	--	%	
Water Absorption				Internal Method
24 hr, 23°C	0.11	--	%	
Equilibrium, 23°C, 50% RH	0.90	--	%	
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	24700	22400	MPa	ISO 527-1/1
Tensile Stress (Break)	249	204	MPa	ISO 527-2/5
Tensile Strain (Break)	1.4	1.4	%	ISO 527-2/5
Flexural Modulus ³	23200	21600	MPa	ISO 178
Flexural Stress ³	429	357	MPa	ISO 178
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179
23°C	14	14	kJ/m²	
Charpy Unnotched Impact Strength				ISO 179
23°C	54	61	kJ/m²	
Thermal	Dry	Conditioned	Unit	Test Method
Deflection Temperature Under Load				
0.45 MPa, Unannealed	237	232	°C	ISO 75-2/B
1.8 MPa, Unannealed	230	223	°C	ISO 75-2/A
CLTE				ISO 11359-2
Flow	1.0E-5	--	cm/cm/°C	
Transverse	4.0E-5	--	cm/cm/°C	

Reny™ 1032H

Mitsubishi Engineering-Plastics Corp - Polyamide MXD6

Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	2.0E+14	8.0E+14	ohms	IEC 60093
Volume Resistivity	2.0E+15	8.0E+14	ohms·cm	IEC 60093
Electric Strength				IEC 60243-1
1.00 mm	26	26	kV/mm	
2.00 mm	20	20	kV/mm	
Dielectric Constant				IEC 60250
1 MHz	--	5.00		
100 MHz	--	6.00		
Dissipation Factor				IEC 60250
1 MHz	--	0.013		
100 MHz	--	0.020		
Comparative Tracking Index	550	> 600	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating (1.6 mm)	HB	--		UL 94

Additional Information

Conditioned Conditioned to 50% RH

Processing Information

Injection	Dry	Unit
Drying Temperature		
Hot Air Dryer, A	120	°C
Hot Air Dryer, B	80	°C
Drying Time		
Hot Air Dryer, A	> 3.0	hr
Hot Air Dryer, B	> 12	hr
Rear Temperature	265	°C
Middle Temperature	270	°C
Front Temperature	275	°C
Nozzle Temperature	275	°C
Mold Temperature	120 to 140	°C
Injection Pressure	20.0 to 150	MPa
Injection Rate	Moderate-Fast	
Screw Speed	60 to 150	rpm

Notes

¹ Typical properties: these are not to be construed as specifications.

² 100-mm square

³ 2.0 mm/min

(+) 18816996168

Poncioplastics.com