

Sunprene® FA 63014- High Quality Extrusion Elastomer Automotive Exterior Seals



PRODUCT BULLETIN

Sunprene® FA 63014-

Flexible PVC elastomer extrusion formulation used for profiles requiring ease of processing, excellent weathering, abrasion resistance and a Class "A" surface appearance. Nominal 5 – 10 gloss surface.

Property	Test Method	Value - English		Value - Metric (SI)	
Hardness, Shore A	ASTM D2240 15 sec. Delay	38		38	
Specific Gravity	ASTM D792	1.21		1.21	
Tensile Strength	ASTM D638 20 in/min (500 mm/min), Type IV	1120	psi	7.7	MPa
Elongation	ASTM D638 20 in/min (500 mm/min), Type IV	450	%	450	%
Tear Strength	ASTM D1004 2 in/min (50 mm/min) Die C	79	ppi	13.85	kN/m
Compression Set	ASTM D395 22 hrs. @ 158°F (70°C)	43	%	43	%



Mitsubishi Chemical Performance Polymers, Inc.

(+) 18816996168

Ponciplastics.com

Process Parameters

Barrel Temperatures

Zone - Rear	300 °F
Zone - Center	305 °F
Zone - Center	315 °F
Zone - Front	320 °F
Adaptor	325 °F
Dies	330 °F

Melt

Temperature	325 °F
--------------------	--------

Screen Pack	20/40/20
--------------------	----------



Mitsubishi Chemical Performance Polymers, Inc.

(+) 18816996168

Poncioplastics.com