

Product Data Sheet
TREXPENE® A40CW
 PP/EPDM Based Vulcanized TPR

Product Description: TREXPENE® A40CW is a UV, heat stabilized PP/EPDM based Thermoplastic Vulcanized Elastomer (TPV). This pre-colored compound is intended primarily for applications needing good compression set properties, excellent aesthetics and UV characteristics. This material can be processed using Injection Molding, Extrusion, Blow Molding or other melt processing techniques.

Property	Test Method	Unit	Typical Values
Hardness	ISO 868	Shore A (15 second delay)	41±3
Density	ISO 1183	g/cm ³	0.91±0.03
Tensile Strength, perpendicular to flow	ISO 37, Type 1, 500mm/min	MPa	3.0 (435 psi)
Tensile Stress at 100%, perpendicular to flow	ISO 37, Type 1, 500mm/min	MPa	1.1 (160 psi)
Ultimate Elongation, perpendicular to flow	ISO 37, Type 1, 500mm/min	%	300
Tear Strength, perpendicular to flow	ISO 34-1, Method B, 500 mm/min	N/mm	12.0 (68 lbf)
Compression Set at 125°C/70hrs 70°C/22hrs	ASTM D395-B, ISO 815-A	%	20 30
Brittle Temperature	ASTM D746, ISO 812B	°C	-56
Long Term Heat Aging Performance	1000 h @ 135°C followed by applicable test method	Hardness Change % Tensile Change % Elongation Change % Tensile @ 100% Elongation change	±5 +10 to -25 +10 to -30 ±20
Short Term Heat Aging Performance	168 h @ 150°C followed by applicable test method	Hardness Change % Tensile Change % Elongation Change % Tensile @ 100% Elongation change	±3 +10 to -20 +10 to -25 ±20
Ozone Resistance	ISO 1431-1, "A" 100pphm, 40°C	Rating	0